

FI 11 Ductflex™

Lightweight flexible blanket

Product description and typical applications

Ductflex™ is a lightweight roll product suitable for insulating flexible ducting of all types. The use of long, fine fibres in the manufacture of Ductflex enables the product to recover to its designed thickness even after prolonged periods of storage on fully compressed duct.

Duct insulated with this product will comply with the requirements of AS4254 "Ductwork for Air-handling Systems in Buildings" and AS4508 "Thermal Resistance of Insulation for Ductwork used in Building Air Conditioning".

Physical characteristics

Material R-value (m ² K/W)	0.6	1.0	1.5	1.8	2.0
Thickness (mm)	25	45	63	75	85
Roll Dimensions (mm)*	30m x various	30m x various	24m x various	24m x various	24m x various
Density (kg/m ³)	11	11	11	11	11
Mass/Unit Area (kg/m ²)	0.3	0.5	0.7	0.8	0.9

NOTE: Ductflex have a perforated cut (Skipchop) at 6 metre intervals to aid installation onto flexible duct cores. Roll widths manufactured to suit 8" (200mm) - 20" (550mm) diameter flexible ducts.

Maximum service temperature

The maximum service temperature for FI 11 Ductflex is 340°C. When used in conjunction with flexible ductwork the temperature tolerance of the core and sleeve will limit this temperature.

Green Star compliant

Fletcher Insulation is committed to providing environmentally sustainable products. Fletcher Insulation products have Zero Ozone Depleting Potential in both manufacture and composition, complying with the GreenStar Insulant ODP Emissions credit requirement. Air quality is maintained with total Volatile Organic Compound (VOC) emissions below quantifiable levels.

AS/NZS 4859.1:
2002 - Including
Amendment 1
Materials for the
Thermal Insulation of
Buildings

FI 11 Ductflex rolls
comply with the Energy
Efficiency provisions of
the BCA for all types
of thermal insulation to
be certified by a NATA
accredited organisation.



Global-Mark.com.au®
ID Number: 100577



Global-Mark.com.au®



DUCTFLEX™

Fletcher™
Insulation

We safely deliver extraordinary
value to our customers

AS1530.1 Test for combustibility of materials

Testing conducted by CSIRO in accordance with AS1530 Part 1 concluded that FI 11 Ductflex is non-combustible.

AS1530.3 Early fire hazard properties of materials

FI 11 Ductflex exhibits the following characteristics when tested in accordance with AS1530 Part 3.

Ignitability Index	0
Spread of Flame Index	0
Heat Evolved Index	0
Smoke Developed Index	0-1

Moisture absorption

Tested in an atmosphere of 65% relative humidity at 20°C in accordance with British Standard 2972. The moisture content of FI 11 Ductflex is less than 0.1% by volume.

Specification notes

State the following:

- Product name - Fletcher Insulation FI 11 Ductflex
- Material R-value required.



The production of environmentally sustainable FBS-1 Glasswool Bio-Soluble Insulation utilizes approximately 70% recycled waste glass.



Low Allergen content with the ability to moderate temperature changes.



Fletcher Insulation glasswool products are manufactured from FBS-1 Bio-Soluble Glass Wool™. FBS-1 Bio-Soluble Glass Wool™ is not classified as hazardous according to the criteria of the Australian Safety and Compensation Council (formerly NOHSC), Approved Criteria for Classifying Hazardous Substances (NOHSC: 1008) 3rd Edition. Fletcher Insulation glasswool is classified as safe to use, refer to our MSDS.



Fletcher[™]
Insulation

Freecall SALES **1300 65 44 44** Technical Services **1800 000 878**
Email info@insulation.com.au Web www.insulation.com.au

NOTE: Fletcher Insulation Pty. Limited. reserves the right to change product specifications without prior notification. Information in this Publication and otherwise supplied to users as to the subject product is based on our general experience and is given in good faith, but Because of the many particular factors which are outside our knowledge and control and affect the use of products, no warranty is given Or is to be implied with respect to either such information or the product itself, in particular the suitability of the product for any particular purpose. The purchaser should independently determine the suitability of the product for the intended application.

Fletcher Insulation Pty. Limited. ABN 72 001 175 355. [™]Trademarks of Fletcher Insulation. [™]FBS-1 Bio-Soluble Glass Wool is a trademark used under license by Fletcher Insulation. © Copyright 2010.